

# WAX TEST INFO #2



Place: **Beitostølen**

Date : **08.12.2022**

Testers: MS, ML

## Glide Test time: 10.30 to 10.50

| Rank | Ski# | Glidewax /  | Feeling |
|------|------|---|---------|
| 1.   | 621  | TSP05 ironed 200C                                 |         |
| 2.   | 23   | TSP05 / TST05 applied with T18W roto wool         |         |
| 2.   | 42   | TSP05 / DHFF applied with T18W roto wool          |         |
| 4.   | 640  | DHP ironed 200C                                   |         |
| 5.   | 809  | TSP05 / TS10 Liq. applied with T18F-2 roto fleece |         |
| 6.   | 808  | TSP05 / TS06 Liq. applied with T18F-2 roto fleece |         |
| 7.   | 43   | TSP05 / HS06 Liq. applied with T18F-2 roto fleece |         |
| 8.   | 807  | PS Polar Powder applied with 200C                 |         |

ALWAYS use recommended respiratory protection when applying glide products.

## Structure

Very fine .... Fine .... Medium .... Coarse ....

## Kick Test time: 10.50 to 11.15

| Rank | Ski# | Wax<br>(base) | Wax<br>(top) | Kick | Feeling |
|------|------|---------------|--------------|------|---------|
| 1.   | A11A | VG30          | V20          | Good | 1       |
| 1.   | A12B | VG30          | V30          | Good | 1       |
| 1.   | A13A | VG30          | VP40         | Good | 1       |
| 4.   | A12A | VG30          | VP30         | Good | 4       |

## Snow and weather info Measurement time: 10.50

|                                    |       |                             |           |
|------------------------------------|-------|-----------------------------|-----------|
| Snow temperature (°C):             | -10,4 | Clouds (sky parts covered): | 6/8       |
| Air temperature (°C):              | -8,3  | Visibility:                 | Unlimited |
| Snow humidity (ref. Doser instr.): | 26    | Wind:                       | Calm      |
| Air humidity (% rH):               | 97    | Precipitation:              | None      |

| ARTIFICIAL SNOW  | NATURAL SNOW  | GRAIN SIZE   | SNOW HUMIDITY  | TRACK HARDNESS   | TRACK CONSISTENCE   |
|--|---|--|--|--|---|
| <ul style="list-style-type: none"><li>o A1 Falling new</li><li>o A2 New</li><li>o A3 Irreg. dir. new</li><li>o A4 Irreg. dir. transf.</li><li>o A5 Transformed</li></ul> | <ul style="list-style-type: none"><li>o FN Falling new</li><li>o <b>NS New</b></li><li>o IN Irreg. dir. new</li><li>o IT Irreg. dir. transf.</li><li>o TR Transformed</li></ul> | <ul style="list-style-type: none"><li>o G0 0.0 - 0.2 mm. Extra fine</li><li>o G1 0.2 - 0.5 mm. Very fine</li><li>o <b>G2 0.5 - 1.0 mm. Fine</b></li><li>o G3 1.0 - 2.0 mm. Average</li><li>o G4 2.0 - 4.0 mm. Coarse</li><li>o G5 &gt; 4.0 mm. Very coarse</li></ul> | <ul style="list-style-type: none"><li>o <b>DS Dry</b></li><li>o W1 Moist</li><li>o W2 Wet</li><li>o W3 Very wet</li><li>o W4 Slush</li></ul> | <ul style="list-style-type: none"><li>o H1 Very soft</li><li>o H2 Soft</li><li>o <b>H3 Med. hard</b></li><li>o H4 Hard</li><li>o H5 Very hard</li><li>o H6 Ice</li></ul> | <ul style="list-style-type: none"><li>o T1 Partly shiny</li><li>o T2 Shiny</li><li>o D1 Partly dirty</li><li>o D2 Dirty</li></ul> |