

WAX TEST INFO #13



Place: Planica

Date: 03.03.2023

Testers: MS, ML

Glide Test time: 09.45 to 10.10

Rank	Ski#	Glidewax / Top	Feeling
1.	18	TSP10 200°C / TS08 Liq. applied with T18F-2 roto fleece	
2.	16	TSP10 200°C	
3.	22	TSP10 200°C / TST10 applied with T18W roto wool	
4.	21	TSP10 200°C / TST08 applied with T18W roto wool	
5.	10	TSP07 200°C	
6.	19	TSP10 200°C / TS10 Liq. applied with T18F-2 roto fleece	

ALWAYS use recommended respiratory protection when applying glide products.

Structure

Very fine Fine Medium Coarse

Kick Test time: 10.30 to 10.50

Rank	Ski#	Wax (base)	Wax (top)	Kick	Feeling
1.	A3A	KX20	KX40S	Good	1
2.	A3B	KX20	VP70	Good	2
3.	A2B	KX20 + KX55	VP50	Good	3
4.	A2A	KX20 + KX35	VP50		

We will continue testing until start.

Snow and weather info Measurement time: 10.10

Snow temperature (°C):	0,0	Clouds (sky parts covered):	8/8
Air temperature (°C):	2,0	Visibility:	1000 m.
Snow humidity (ref. Doser instr.):	22-31	Wind:	Calm
Air humidity (% rH):	87	Precipitation:	None

ARTIFICIAL SNOW	NATURAL SNOW	GRAIN SIZE	SNOW HUMIDITY	TRACK HARDNESS	TRACK CONSISTENCE
<ul style="list-style-type: none">o A1 Falling newo A2 Newo A3 Irreg. dir. newo A4 Irreg. dir. transf.o A5 Transformed	<ul style="list-style-type: none">o FN Falling newo NS Newo IN Irreg. dir. newo IT Irreg. dir. transf.o TR Transformed	<ul style="list-style-type: none">o G0 0.0 - 0.2 mm. Extra fineo G1 0.2 - 0.5 mm. Very fineo G2 0.5 - 1.0 mm. Fineo G3 1.0 - 2.0 mm. Averageo G4 2.0 - 4.0 mm. Coarseo G5 > 4.0 mm. Very coarse	<ul style="list-style-type: none">o DS Dryo W1 Moisto W2 Weto W3 Very weto W4 Slush	<ul style="list-style-type: none">o H1 Very softo H2 Softo H3 Med. hardo H4 Hardo H5 Very hardo H6 Ice	<ul style="list-style-type: none">o T1 Partly shinyo T2 Shinyo D1 Partly dirtyo D2 Dirty