

# WAX TEST INFO #3



Place: Planica

Date: 22.02.2023

Testers: MS, ML

## Glide

Test time: 13.50 to 14.10

Rank	Ski#	Glidewax / Top	Feeling
1.	16	TSP10 200°C / TS10 Liq. applied with T18F-2 roto fleece	
2.	18	I84N (cleaner) / TS10 Liq. applied with T18F-2 roto fleece	
3.	10	I84N (cleaner) / TST10 applied with T18W roto wool	
4.	19	I84N (cleaner) / HS10 Liq. applied with T18F-2 roto fleece	

ALWAYS use recommended respiratory protection when applying glide products.

## Structure

Very fine .... Fine .... Medium .... Coarse ....

## Kick

Test time: to

Rank	Ski#	Wax (base)	Wax (top)	Kick	Feeling
------	------	---------------	--------------	------	---------

## Snow and weather info

Measurement time: 14.20

Snow temperature (°C):	0,0	Clouds (sky parts covered):	3/8
Air temperature (°C):	4,5	Visibility:	Unlimited
Snow humidity (ref. Doser instr.):	85-100	Wind:	Calm
Air humidity (% rH):	73	Precipitation:	None

ARTIFICIAL SNOW	NATURAL SNOW	GRAIN SIZE	SNOW HUMIDITY	TRACK HARDNESS	TRACK CONSISTENCE
<ul style="list-style-type: none"><li>o A1 Falling new</li><li>o A2 New</li><li>o A3 Irreg. dir. new</li><li>o A4 Irreg. dir. transf.</li><li>o A5 Transformed</li></ul>	<ul style="list-style-type: none"><li>o FN Falling new</li><li>o NS New</li><li>o IN Irreg. dir. new</li><li>o IT Irreg. dir. transf.</li><li>o TR Transformed</li></ul>	<ul style="list-style-type: none"><li>o G0 0.0 - 0.2 mm. Extra fine</li><li>o G1 0.2 - 0.5 mm. Very fine</li><li>o G2 0.5 - 1.0 mm. Fine</li><li>o G3 1.0 - 2.0 mm. Average</li><li>o G4 2.0 - 4.0 mm. Coarse</li><li>o G5 &gt; 4.0 mm. Very coarse</li></ul>	<ul style="list-style-type: none"><li>o DS Dry</li><li>o W1 Moist</li><li>o W2 Wet</li><li>o W3 Very wet</li><li>o W4 Slush</li></ul>	<ul style="list-style-type: none"><li>o H1 Very soft</li><li>o H2 Soft</li><li>o H3 Med. hard</li><li>o H4 Hard</li><li>o H5 Very hard</li><li>o H6 Ice</li></ul>	<ul style="list-style-type: none"><li>o T1 Partly shiny</li><li>o T2 Shiny</li><li>o D1 Partly dirty</li><li>o D2 Dirty</li></ul>